



EUROPEAN PATENT APPLICATION

(51) Int. Cl.⁶: **C08G 73/00**, C08G 18/02,
C08G 18/79

(22) Date of filing: 12.03.1999

(71) Applicant:
Nisshinbo Industries, Inc.
Chuo-ku, Tokyo 103-8650 (JP)


(72) Inventors:

- **Amano, Satoshi,**
Nisshinbo Industries, Inc.
Adachi-ku, Tokyo 123-0843 (JP)
- **Nakamura, Norimasa**
Adachi-ku, Tokyo 123-0843 (JP)

(74) Representative:
Laufhütte, Dieter, Dr.-Ing. et al
Lorenz-Seidler-Gossel
Widenmayerstrasse 23
80538 München (DE)

(54) Polycarbodiimide copolymer and process for production thereof

(57) There are provided a polycarbodiimide copolymer having a main structure represented by the following formula (1):



wherein R₁ is an isocyanate residue; R₂ is a polyfunctional liquid rubber residue; X is a urethane bond, an amide bond or a urea bond; p is an integer of 5 to 50; q is an integer of 1 to 5; and r is 0 or 1; and a process for producing the above polycarbodiimide copolymer, which comprises reacting a polyfunctional liquid rubber with an organic diisocyanate in excess of the rubber and then subjecting the diisocyanate components in the reaction system to carbodiimidization using a carbodiimidization catalyst. The polycarbodiimide copolymer alleviates the problems of the prior art, has the excellent heat resistance inherently possessed by polycarbodiimide resins, is improved, as compared with conventional polycarbodiimide resins, in thermoformability under heating and pressure when made into a solid such as powder or granule, and causes no blistering under heating.

[0008] According to the present invention there is also provided a process for producing the above polycarbodiimide copolymer, which process comprises reacting a polyfunctional liquid rubber with an organic diisocyanate of large excess over the rubber and then subjecting the diisocyanate components in the reaction system to carbodiimidization using a carbodiimidization catalyst.

Brief Description of the Drawings

[0009]

Fig. 1 is an IR spectrum of the polycarbodiimide copolymer produced in Example 1.

Fig. 2 is an IR spectrum of the polycarbodiimide copolymer produced in Example 3.

Fig. 3 is an IR spectrum of the polycarbodiimide copolymer produced in Example 5.

Fig. 4 is an IR spectrum of the polycarbodiimide copolymer produced in Example 6.

Detailed Description of the Invention

[0010] The present invention is hereinafter described in detail.

[0011] The polycarbodiimide copolymer of the present invention has a main structure represented by the above-mentioned formula (1). In the formula (1), R_1 is an isocyanate residue; R_2 is a polyfunctional liquid rubber residue; and X is a urethane bond, an amide bond or a urea bond.

[0012] The isocyanate residue (R_1) refers to a structure formed when two isocyanates are removed from an organic diisocyanate. The polyfunctional liquid rubber residue (R_2) refers to a structure formed when a plurality of functional groups for formation of urethane bond, amide bond or urea bond are removed from a polyfunctional liquid rubber.

[0013] The organic diisocyanate used in the present invention may be an aromatic or aliphatic diisocyanate. An aromatic diisocyanate is preferred from the standpoint of reaction control.

[0014] Examples of the aromatic diisocyanate include 4,4'-diphenylmethane diisocyanate, 4,4'-diphenyl ether diisocyanate, p-phenylene diisocyanate, m-phenylene diisocyanate, 3,3'-dimethoxy-4,4'-biphenyl diisocyanate, o-tolidine diisocyanate, naphthylene diisocyanate, 2,4'-tolylene diisocyanate and 2,6'-tolylene diisocyanate.

[0015] Examples of the aliphatic diisocyanate include hexamethylene diisocyanate, 2,2,4-trimethylhexamethylene diisocyanate, 4,4'-dicyclohexylmethane diisocyanate, xylylene diisocyanate, tetramethylxylylene diisocyanate, isophorone diisocyanate, cyclohexyl diisocyanate, lysine diisocyanate and methylcyclohexane-2,4-diisocyanate.

[0016] The polycarbodiimide copolymer of the present invention can be obtained in the form of, for example, varnish, powder or granule. When obtained in the form of powder or granule, the organic diisocyanate used is preferably solid at around room temperature (20°C).

[0017] The organic diisocyanate which is solid at around room temperature, can be exemplified by 4,4'-diphenylmethane diisocyanate, o-tolidine diisocyanate, 4,4'-diphenyl ether diisocyanate and phenylene diisocyanate. Of these, 4,4'-diphenylmethane diisocyanate is particularly preferred in view of the wide usability. These diisocyanates may be used singly or in admixture of two or more kinds.

[0018] The polyfunctional liquid rubber used in the present invention is a liquid rubber having, in the molecule, two or more functional groups reactive with isocyanate. Such functional groups include -OH, -COOH, -NH₂-NHR, -SO₃H, -SH, -NHCONH₂, -NHCOOR, etc. Of these, -OH, -COOH, -NH₂ and -NHR are particularly preferred in view of the reactivity and utilizability.


[0019] In order for the present invention to be able to exhibit the merit effectively, the polyfunctional liquid rubber is desired to have a molecular weight of 200 or more. When the molecular weight is less than 200, the resulting polycarbodiimide copolymer has low flexibility; moreover, the unreacted low-molecular compounds in the copolymer vaporize during the thermoforming of the copolymer and gives, in some cases, an adverse effect on the molded product.

[0020] The polyfunctional liquid rubber can be exemplified by liquid polybutadienes [e.g. Hycar CTB (trade name) of Ube Industries, Ltd. and Nisso PB (trade name) of Nippon Soda Co., Ltd.], liquid polybutadiene-acrylonitrile copolymers [e.g. Hycar CTBN and ATBN (trade names) of Ube Industries, Ltd.], liquid polyisoprenes [e.g. Kuraprene LIR-403 (trade name) of Kuraray Co., Ltd.], liquid hydrogenated polyisoprenes, liquid polysulfides and liquid silicones. Of course, modification products thereof can also be used.


[0021] Of the above polyfunctional liquid rubbers, Kuraprene LIR-403 (trade name) of Kuraray Co., Ltd. has three carboxyl groups in the molecule.

[0022] The polyfunctional liquid rubber residue (R_2) can be exemplified by the following residues.


[0023] Residue of liquid polybutadiene-acrylonitrile copolymer:



[0024] Residue of liquid polybutadiene:



[0025] Residue of liquid polyisoprene:



[0026] In the above formulas, x, y and z refer to the following integers.

[0027] In the liquid polybutadiene-acrylonitrile copolymer,

$$4 \leq (x+y), 1 \leq z$$

in the polybutadiene,

$$4 \leq x$$

and in the polyisoprene,

$$3 \leq x$$

[0028] In the formula (1), p (which indicates the polymerization degree of the moiety structure NCN-R_1) is an integer of 5 to 50. When p is less than 5, the resulting polycarbodiimide copolymer has no properties inherently possessed by polycarbodiimide resins and is impossible to take out in the form of powder or granule. When p is more than 50, it is highly probable that the resulting polycarbodiimide copolymer causes gelation during the synthesis.

[0029] In the formula (1), q (which indicates the polymerization degree of the moiety structure $[\text{R}_1-\text{X}-\text{R}_2-\text{X}-\text{R}_1-(\text{NCN}-\text{R}_1)_p]_q$) is an integer of 1 to 5. When q is 0, the resulting polycarbodiimide copolymer is a conventional polycarbodiimide and is not a polymer of the formula (1). When q is more than 5, the resulting polycarbodiimide copolymer has too large a molecular weight and it is highly probable that the copolymer causes gelation during the synthesis.

[0030] In the formula (1), r (which indicates the polymerization degree of the moiety structure $[\text{X}-\text{R}_1-(\text{NCN}-\text{R}_1)_p-\text{NCO}]_r$) is 0 or 1. When r is 0, the resulting copolymer is a linear polycarbodiimide copolymer of the present invention. When r is 2 or more, the resulting copolymer has many crosslinking sites and it is highly probable that the copolymer causes gelation during the synthesis or the storage.

[0031] The polycarbodiimide copolymer of the present invention can be produced by the production process of the present invention which comprises reacting a polyfunctional liquid rubber with an organic diisocyanate in excess of the rubber and then subjecting the diisocyanate components in the reaction system to carbodiimization using a carbodiimidization catalyst.

[0032] The organic diisocyanate and polyfunctional liquid rubber both used in the production process of the present invention have been described above.

[0033] "The diisocyanate components in the reaction system" refer mainly to

1. the organic diisocyanate which did not take part in the reaction, and
2. polyfunctional liquid rubber derivatives having, in the molecule, two or more isocyanate groups, formed by the reaction of the polyfunctional liquid rubber with the organic diisocyanate, and further to
3. a polyfunctional liquid rubber derivative having one isocyanate group in the molecule, formed by the reaction of the polyfunctional liquid rubber with the organic diisocyanate.

[0034] The probability of the presence of the derivative 3 is very low. The derivative 3 reacts with the organic diisocyanate 1 which did not take part in the reaction (i.e. excessive organic diisocyanate), and becomes the derivative 2 and is carbodiimidized.

[0035] In the present production process, the organic diisocyanate is used in an excess of the polyfunctional liquid rubber. This "excess" can be as follows, for example.

$$7 \leq (\text{number of isocyanate groups}) / (\text{number of active hydrogen atoms in polyfunctional liquid rubber})$$

[0036] The present production process is characterized in that an organic diisocyanate is reacted with a polyfunctional liquid rubber and then a carbodiimidization catalyst is added to synthesize a polycarbodiimide copolymer. If this sequence is reversed and the reaction with a polyfunctional liquid rubber is conducted during or after the synthesis of a polycarbodiimide resin, the functional groups of liquid rubber react not only with isocyanate group but also with carbodiimide group and gelation takes place at a high probability, making it very difficult to obtain an intended copolymer.

[0037] The reaction of organic diisocyanate with polyfunctional liquid rubber in the present production process can be conducted in bulk (using no solvent) because the reaction system causes no solidification or gelation during the reaction. If the reaction system causes solidification or gelation during the bulk reaction of the two materials, an appropriate solvent may be used in the reaction.

[0038] The solvent is preferably one capable of dissolving all of the organic diisocyanate (raw material), the polyfunctional liquid rubber (raw material), reaction products thereof and polycarbodiimide copolymers obtained by carbodiimidization of the reaction products. Such a solvent includes, for example, alicyclic ethers (e.g. tetrahydrofuran and dioxane) and aromatic hydrocarbons (e.g. benzene and toluene). Of these, tetrahydrofuran is particularly preferred. These solvents may be used singly or in admixture of two or more kinds.

[0039] The reaction temperature used in the reaction of the organic diisocyanate with the polyfunctional liquid rubber is preferably 30 to 180°C although it differs depending upon the kind of functional group reacted with isocyanate group. The reaction temperature is more preferably 50 to 150°C when the shortening of reaction time or the prevention of thermal degradation of liquid rubber is taken into consideration. When a reaction solvent is used, the reaction temperature is desirably 50°C to the boiling point of solvent.

[0040] The temperature of carbodiimidization reaction is determined by the kind of solvent and the concentrations of monomers but is preferably 50°C to the boiling point of solvent.

[0041] The carbodiimidization catalyst can be a known catalyst and includes, for example, phosphorene oxides such as 3-methyl-1-phenyl-2-phosphorene-1-oxide, 3-methyl-1-phenyl-3-phosphorene-1-oxide, 3-methyl-1-ethyl-2-phosphorene-1-oxide and the like. Of these, 3-methyl-1-phenyl-2-phosphorene-1-oxide is preferred for the reactivity. The amount of the catalyst is preferably 0.1 to 1.0% by weight based on the organic diisocyanate used.

[0042] The solid content in the carbodiimidization is preferably 5 to 50% by weight among the total weight of the reaction system, more preferably 20 to 30% by weight. When the solid content is less than 5% by weight, a large amount of a poor solvent is required (this is uneconomical) when, as mentioned later, the poor solvent is added to precipitate a polycarbodiimide copolymer. When the solid content is more than 50% by weight, gelation or solidification takes place at a high probability in the course of polymerization (this brings about inconvenience).

[0043] For obtaining the polycarbodiimide copolymer of the present invention in the form of powder or granule, a known method can be used. That is, to the polycarbodiimide copolymer solution is added a poor solvent to the copolymer to precipitate the copolymer in the form of solid, and the precipitate is filtered or subjected to spray drying to obtain a powder or granules.

[0044] The poor solvent is preferably a poor solvent having a boiling point as low as possible, in view of the economy of drying the powdery or granular polycarbodiimide copolymer obtained. Such a poor solvent includes, for example, aliphatic hydrocarbons, esters, ethers and ketones. Specifically, the aliphatic hydrocarbons are pentane, hexane, heptane, octane, nonane, etc.; the esters are methyl acetate, ethyl acetate, isopropyl acetate, butyl acetate, ethyl propionate, methyl butyrate, ethyl butyrate, etc.; the ethers are diethyl ether, dibutyl ether, isopropyl ether, etc.; and the ketones are acetone, methyl ethyl ketone, diethyl ketone, methyl propyl ketone, methyl isobutyl ketone, methyl isopropyl ketone, etc. These solvents can be used singly or in admixture of two or more kinds.

[0045] The amount of poor solvent added varies depending upon the kind of poor solvent and the solid content in polycarbodiimide copolymer solution, but is appropriately 0.5 to 10 times the weight of polycarbodiimide copolymer

solution. When the amount of poor solvent used is less than 0.5 time the weight of polycarbodiimide copolymer solution, it is difficult to obtain the polycarbodiimide copolymer in the form of powder or granule. When the amount is more than 10 times, the productivity of polycarbodiimide copolymer is low.

[0046] The timing of addition of the poor solvent may be right after the polymerization reaction or after cooling of the polycarbodiimide copolymer solution. In order to achieve quick precipitation of powder or granule, it is preferred that the polycarbodiimide copolymer solution is cooled to 5 to 20°C, then the poor solvent is added, and stirring is conducted at 5 to 20°C for 1 to 10 hours.

[0047] Of course, the polycarbodiimide copolymer produced in the present process can be obtained also in the form of, for example, varnish.

[0048] It is easily anticipated that by using the present production process, a terminal-blocked polycarbodiimide copolymer and a powder thereof can be produced as well.

[0049] The polycarbodiimide copolymer produced by the present process can be applied as, for example, a modifier (e.g. adhesivity improver or heat resistance improver) for epoxy resin or phenolic resin. It is also possible to mold the resulting mixture (mixture of epoxy or phenolic resin and polycarbodiimide copolymer) by a known molding method such as transfer molding, extrusion molding, compression molding, injection molding or the like to use the molded product in various industrial applications.

[0050] The present invention is described in more detail below by way of Examples. However, the present invention is not restricted to these Examples.

Example 1

[0051] Into a 3-liter separable flask provided with a stirrer and a condenser was fed 150 g of 4,4'-diphenylmethane diisocyanate (hereinafter referred to as "MDI") dissolved in 400 g of tetrahydrofuran (hereinafter referred to as "THF"). Thereto was dropwise added, at room temperature, a solution of 21.6 g of ATBN (trade name) (amine-terminated NBR marketed by Ube Industries, Ltd.) dissolved in 200 g of THF. After the completion of the dropwise addition, a reaction was conducted at 75°C for 4 hours. The reaction mixture was measured for IR spectrum, which indicated absorption of urea at 1,638 cm^{-1} . Then, 0.45 g of 3-methyl-1-phenyl-2-phosphorene-1-oxide was added, and a carbodiimidization reaction was conducted at 75°C for 5.5 hours. The reaction mixture was measured for IR spectrum, which indicated absorption of carbodiimide at 2,110 cm^{-1} as shown in Fig. 1. Thereafter, the system was cooled and, when the solution temperature became 10°C, 800 g of n-hexane was added with stirring. After continuing cooling and stirring for a while, a slurry was obtained. The slurry was subjected to vacuum filtration using a Buchner funnel to obtain a wet cake. The wet cake was placed in a mortar, disintegrated gently, and dried at 70°C under vacuum for 5 hours to obtain a white powder. The powder was measured for melting point by DSC, and the melting point was 121°C. This powder was judged to be a copolymer of the formula (1) wherein x = urea bond, p = 25, q = 1 and r = 0. The copolymer was also measured for number-average molecular weight, and the molecular weight (M_n) was 4.1×10^3 (a value measured by gel permeation chromatography and polystyrene-reduced, the same applies hereinafter as well).

Example 2

[0052] The same synthesis apparatus as used in Example 1 was used. From the material inlet of the apparatus were fed 240 g of MDI and 33.6 g of CTBN (trade name) (a carboxyl-terminated NBR marketed by Ube Industries, Ltd.). A reaction was conducted at 130°C for 5 hours. Thereto were added 560 g of THF and 0.48 g of 3-methyl-1-phenyl-2-phosphorene-1-oxide, and a carbodiimidization reaction was conducted at 75°C for 2.75 hours. The reaction mixture was measured for IR spectrum, which indicated absorption of carbodiimide at 2,110 cm^{-1} . After the completion of the reaction, the system was cooled. When the solution temperature became 10°C, 1,000 g of n-hexane was added. After continuing cooling and stirring, a slurry was obtained. The slurry was filtered. The solid obtained was placed in a mortar, disintegrated gently, and dried at 70°C under vacuum for 5 hours to obtain a white powder. The powder was measured for melting point by DSC, and the melting point was 116°C. This powder was judged to be a copolymer of the formula (1) wherein x = amide bond, p = 50, q = 1 and r = 0. The copolymer was also measured for number-average molecular weight, and the molecular weight (M_n) was 4.4×10^3 .

Example 3

[0053] The same synthesis apparatus as used in Example 1 was used. From the material inlet of the apparatus were fed 125 g of MDI and 48 g of CTB (trade name) (a carboxyl-terminated liquid polybutadiene marketed by Ube Industries, Ltd.). A reaction was conducted at 130°C for 5 hours. The reaction mixture was measured for IR spectrum, which indicated absorption of amide at 1,640 cm^{-1} . Then, 500 g of THF and 0.25 g of 3-methyl-1-phenyl-2-phosphorene-1-oxide were added, and a carbodiimidization reaction was conducted at 75°C for 4.5 hours. The reaction mixture was meas-

ured for IR spectrum, which indicated absorption of carbodiimide at $2,110\text{ cm}^{-1}$ as shown in Fig. 2. After the completion of the reaction, the system was cooled. When the solution temperature became 10°C , 1,000 g of acetone was added. After continuing cooling and stirring, a slurry was obtained. The slurry was filtered. The solid obtained was placed in a mortar, disintegrated gently, and dried at 70°C under vacuum for 5 hours to obtain a white powder. The powder was measured for melting point by DSC, and the melting point was 132°C . This powder was judged to be a copolymer of the formula (1) wherein $x = \text{amide bond}$, $p = 25$, $q = 1$ and $r = 0$. The copolymer was also measured for number-average molecular weight, and the molecular weight (M_n) was 4.6×10^3 .

Example 4

[0054] The operation of Example 3 was repeated except that the amount of CTB used was changed to 24 g. The white powder obtained was judged to be a copolymer of the formula (1) wherein $x = \text{amide bond}$, $p = 50$, $q = 1$ and $r = 0$. The copolymer was also measured for number-average molecular weight, and the molecular weight (M_n) was 4.4×10^3 .

Example 5

[0055] The same synthesis apparatus as used in Example 1 was used. From the material inlet of the apparatus were fed 300 g of MDI and 22.4 g of TL-20 (trade name) (a hydroxyl-terminated liquid polyisoprene produced by Kuraray Co., Ltd.). A reaction was conducted at 100°C for 4.5 hours. The reaction mixture was measured for IR spectrum, which indicated absorption of urethane at $1,730\text{ cm}^{-1}$. Then, 700 g of THF and 0.6 g of 3-methyl-1-phenyl-2-phosphorene-1-oxide were added, and a carbodiimidization reaction was conducted at 70°C for 3 hours. The reaction mixture was measured for IR spectrum, which indicated absorption of carbodiimide at $2,110\text{ cm}^{-1}$ as shown in Fig. 3. After the completion of the reaction, the system was cooled. When the solution temperature became 10°C , 530 g of n-hexane was added. After continuing cooling and stirring, a slurry was obtained. The slurry was filtered. The solid obtained was placed in a mortar, disintegrated gently, and dried at 70°C under vacuum for 5 hours to obtain a white powder. The powder was measured for melting point by DSC, and the melting point was 133°C . This powder was judged to be a copolymer of the formula (1) wherein $x = \text{urethane bond}$, $p = 50$, $q = 1$ and $r = 0$. The copolymer was also measured for number-average molecular weight, and the molecular weight (M_n) was 4.0×10^3 .

Example 6

[0056] The same synthesis apparatus as used in Example 1 was used. From the material inlet of the apparatus were fed 300 g of MDI and 32.4 g of TH-2 (trade name) (a hydroxyl-terminated liquid hydrogenated polyisoprene produced by Kuraray Co., Ltd.). A reaction was conducted at 100°C for 3.5 hours. The reaction mixture was measured for IR spectrum, which indicated absorption of urethane at $1,730\text{ cm}^{-1}$. Then, 1,000 g of THF and 0.6 g of 3-methyl-1-phenyl-2-phosphorene-1-oxide were added, and a carbodiimidization reaction was conducted at 70°C for 4.5 hours. The reaction mixture was measured for IR spectrum, which indicated absorption of carbodiimide at $2,110\text{ cm}^{-1}$ as shown in Fig. 4. After the completion of the reaction, the system was cooled. When the solution temperature became 10°C , 1,000 g of n-hexane was added. After continuing cooling and stirring, a slurry was obtained. The slurry was filtered. The solid obtained was placed in a mortar, disintegrated gently, and dried at 70°C under vacuum for 5 hours to obtain a white powder. The powder was measured for melting point by DSC, and the melting point was 126°C . This powder was judged to be a copolymer of the formula (1) wherein $x = \text{urethane bond}$, $p = 40$, $q = 1$ and $r = 0$. The copolymer was also measured for number-average molecular weight, and the molecular weight (M_n) was 4.2×10^3 .

Example 7

[0057] The same synthesis apparatus as used in Example 1 was used. From the material inlet of the apparatus were fed 500 g of tolylene diisocyanate and 107 g of TL-20. A reaction was conducted at 100°C for 5 hours. The reaction mixture was measured for IR spectrum, which indicated absorption of urethane at $1,730\text{ cm}^{-1}$. Then, 1,400 g of THF and 1.0 g of 3-methyl-1-phenyl-2-phosphorene-1-oxide were added, and a carbodiimidization reaction was conducted at 70°C for 8 hours. The reaction mixture was measured for IR spectrum, which indicated absorption of carbodiimide at $2,137\text{ cm}^{-1}$. The copolymer in the varnish obtained was judged to be a copolymer of the formula (1) wherein $x = \text{urethane bond}$, $p = 25$, $q = 1$ and $r = 0$. The copolymer was also measured for number-average molecular weight, and the molecular weight (M_n) was 3.72×10^3 .

Comparative Example 1 (Synthesis of polycarbodiimide powder)

[0058] The same synthesis apparatus as used in Example 1 was used. From the material inlet of the apparatus were

fed 300 g of MDI and 560 g of THF. After MDI dissolved completely, 0.6 g of 3-methyl-1-phenyl-2-phosphorene-1-oxide was added and a carbodiimidization reaction was conducted at 70°C for 3 hours. After the completion of the reaction, the system was cooled. When the solution temperature became 10°C, 1,500 g of ethyl acetate was added. After continuing cooling and stirring, a slurry was obtained. The slurry was filtered. The solid obtained was placed in a mortar, disintegrated gently, and dried at 70°C under vacuum for 5 hours to obtain a white powder. The powder (polymer) was measured for number-average molecular weight, and the molecular weight (M_n) was 4.0×10^3 .

Comparative Example 2 [Synthesis of polycarbodiimide (copolymer) powder]

[0059] The same synthesis apparatus as used in Example 1 was used. From the material inlet of the apparatus were fed 400 g of MDI and 540 g of THF. Thereto was dropwise added a solution of 14.1 g of 1,4-diaminobutane dissolved in 200 g of THF, and a reaction to form a urea bond was conducted for 3 hours. Then, 0.8 g of 3-methyl-1-phenyl-2-phosphorene-1-oxide was added and a carbodiimidization reaction was conducted at 70°C for 4.5 hours. After the completion of the reaction, the system was cooled. When the solution temperature became 10°C, 1,000 g of ethyl acetate was added. After continuing cooling and stirring, a slurry was obtained. The slurry was filtered. The solid obtained was placed in a mortar, disintegrated gently, and dried at 70°C under vacuum for 5 hours to obtain a white powder. The powder (copolymer) was measured for number-average molecular weight, and the molecular weight (M_n) was 3.9×10^3 .

Evaluation of thermoformability of polycarbodiimide copolymers (in conformity to JIS K6911 5.3.2)

[0060] To evaluate the thermoformability of the polycarbodiimide copolymer powders obtained above, each polycarbodiimide copolymer was measured for flowability under heating and pressure, as follows. First, a Teflon glass sheet of 15 cm x 15 cm was placed on a press plate (surface temperature = 155°C); in almost the center thereon was placed a metal cylinder of 3.4 cm in diameter; in the cylinder was placed 1.0 g of a powder of polycarbodiimide copolymer or the like, obtained in one of the above Examples and Comparative Examples; and the cylinder was removed gently (the powder formed a conical shape). Then, on the powder was placed a Teflon glass sheet of 15 cm x 15 cm, and the sheet was pressed for 30 seconds with a force of 1.2 t to obtain a film. The film was measured for major axis length and minor axis length at the luster portion (transparent portion), and the average of the two lengths was calculated and taken as the "flowability" of the polycarbodiimide copolymer.

[0061] To obtain a film having 0.2 mm in thickness, 0.6 - 1.0 g of the powder of polycarbodiimide copolymer or the like obtained in one of the above Examples and Comparative Examples was heat-pressed in a same manner as in above evaluation. The flexibility of the film was examined by bending the above film by 180° and observing the appearance of cracking. The results are shown in Table 1.

[0062] Further, to confirm that the polycarbodiimide copolymer powders obtained above cause no foaming and blistering, the film obtained as above was placed on a press plate (surface temperature = 200°C) without applying pressure for 30 minutes, and a condition of the film was observed visually. The results are shown in Table 1.

Table 1

	Examples						Comp. Ex.	
	1	2	3	4	5	6	1	2
Flowability (mm)	52	69	65	70	76	64	48	- ¹⁾
Flexibility ²⁾	o	o	o	o	o	o	o	x
Foaming or blistering	No	No	No	No	No	No	No	- ³⁾

1) The film was a sheet of white and opaque, and impossible to measure for flowability (in other Examples, a film was obtained.).

2) o: No cracking x: Cracked

3) The film was impossible to measure.

[0063] The polycarbodiimide copolymer of Example 5 and the polycarbodiimide of Comparative Example 1 were measured for film formability (i.e., the lowest formable temperature) when only the surface temperature of press plate was changed, according to the same method as used above. The results are shown in Table 2.

Table 2

		Plate surface temp. (°C)		
		120	130	140
Example 5	Film formability ¹⁾	Δ	o	o
	Flexibility ²⁾	o	o	o
	Flowability (mm)	49	51	58
Comp. Ex. 1	Film formability	--	x	x
	Flexibility	--	x	Δ
	Flowability (mm)	--	3)	3)

1)

o: Film forming is possible.

Δ: Film forming is possible but film transparency is slightly inferior.

x: Film forming is impossible (a white opaque sheet is obtained).

2)

o: No cracking

Δ: Partially cracked

x: Completely cracked

3) Impossible to measure


[0064] As is clear from Table 1, the polycarbodiimide copolymer of the present invention has improved flowability because a polyfunctional liquid rubber structure of high flexibility is introduced into a relatively stiff carbodiimide main chain; therefore, the present polycarbodiimide copolymer has higher thermoformability than conventional polycarbodiimide resins and, moreover, can be made into a film having an excellent flexibility, and causing no foaming and blistering.

[0065] As is also clear from Table 2, the polycarbodiimide copolymer of the present invention can be made into a film even in a temperature range wherein filming of conventional polycarbodiimide resins has been impossible.

[0066] In addition, the process for producing a polycarbodiimide copolymer of the present invention is capable of producing above polycarbodiimide copolymer easily; hence, the present polycarbodiimide copolymer and the process for production thereof have high industrial applicability respectively.

Claims


1. A polycarbodiimide copolymer having a main structure represented by the following formula (1):



wherein R_1 is an isocyanate residue; R_2 is a polyfunctional liquid rubber residue; X is a urethane bond, an amide bond or a urea bond; p is an integer of 5 to 50; q is an integer of 1 to 5; and r is 0 or 1.

2. A polycarbodiimide copolymer according to Claim 1, obtained by reacting a polyfunctional liquid rubber with an organic diisocyanate in excess of the rubber and then subjecting the diisocyanate components in the reaction system to carbodiimidization using a carbodiimidization catalyst.
3. A polycarbodiimide copolymer according to Claim 1, which is powdery or granular.
4. A process for producing a polycarbodiimide copolymer having a main structure represented by the following for-

mula (1):



(wherein R₁ is an isocyanate residue; R₂ is a polyfunctional liquid rubber residue; X is a urethane bond, an amide bond or a urea bond; p is an integer of 5 to 50; q is an integer of 1 to 5; and r is 0 or 1), which process comprises reacting a polyfunctional liquid rubber with an organic diisocyanate in excess of the rubber and then subjecting the diisocyanate components in the reaction system to carbodiimization using a carbodiimidization catalyst.

5. A process according to Claim 4, wherein the polycarbodiimide copolymer is powdery or granular.
6. A process according to Claim 4 or 5, wherein a polymerization solvent is selected from the group consisting of alicyclic ethers, aromatic hydrocarbons and mixtures thereof.

Fig. 1




Fig.2




Fig.3





Fig. 4





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 10 4968

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
A	EP 0 691 379 A (NISSHIN SPINNING) 10 January 1996 * claims 1-23 *	1-6	C08G73/00 C08G18/02 C08G18/79
A	EP 0 189 156 A (BASF CORP) 30 July 1986 * claim 1 *	1-6	
A	EP 0 610 960 A (NISSHIN SPINNING) 17 August 1994 * claims 1-6 *	2,4-6	
A	US 3 929 733 A (ALBERINO LOUIS M ET AL) 30 December 1975 * claims 1-7 *	1-6	
D	& JP 52 016759 B		
			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
			C08G
The present search report has been drawn up for all claims			
Place of search		Date of completion of the search	Examiner
THE HAGUE		25 May 1999	Glanddier, A
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 10 4968

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

25-05-1999

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0691379 A	10-01-1996	US 5849404 A	15-12-1998
		WO 9520012 A	27-07-1995
EP 0189156 A	30-07-1986	CA 1285956 A	09-07-1991
		US 4937012 A	26-06-1990
EP 0610960 A	17-08-1994	JP 2292316 A	03-12-1990
		JP 2769852 B	25-06-1998
		DE 69020797 D	17-08-1995
		DE 69029868 D	13-03-1997
		EP 0398069 A	22-11-1990
		US 5416184 A	16-05-1995
US 3929733 A	30-12-1975	DE 2543920 A	08-04-1976
		FR 2286838 A	30-04-1976
		GB 1464804 A	16-02-1977
		JP 888550 C	10-11-1977
		JP 51061599 A	28-05-1976
		JP 52016759 B	11-05-1977
		NL 7511375 A	06-04-1976

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.